




# Maintenance-Free Rechargeable Sealed Lead-Acid Battery

## BP1.2-12




The battery is constructed by plates, separators, safety valves and container. Since the electrolyte is held by a glass-mat separator and plates, the battery can use in any direction and position without leakage.


### PERFORMANCE SPECIFICATIONS

Nominal Voltage(V).....	12 volts(6cells in series)
Nominal Capacity(AH)	
20 hour rate F.V.(1.75V/cell)( 60mA to 10.50volts) .....	1.2A.H.
10 hour rate F.V.(1.75V/cell)( 114mA to 10.50volts).....	1.14A.H.
5 hour rate F.V.(1.75V/cell)( 204mA to 10.50volts) .....	1.02A.H.
1 hour rate F.V.(1.55V/cell)( 720mA to 9.30volts).....	0.72A.H.
Approximate Weight.....	590g(1.30lbs.)
Terminal	
Standard.....	T1
Internal Resistance (Fully Charged Battery).....	<120mΩ
Maximum Discharge Current For 5 sec.(A).....	18A
Maximum Charge Current(A).....	0.36A
Ambient Temperature	
Charge.....	0°C(32°F)~40°C(104°F)
Discharge.....	-20°C(-4°F)~50°C(122°F)
Storage.....	-20°C(-4°F)~40°C(104°F)
Vibration test:	
Frequency: 16.7HZ	
Amplitude: 4mm	
Vibrate the battery horizontally or vertically for 60 minutes. The battery have no abnormality.	
Case.....	ABS
Dimension(mm/inch)	
Length           ±1.5mm.....	97/3.82
Width           ±1.5mm.....	45/1.77
Container Height ±1.5mm.....	53/2.09
Total Height    ±2mm.....	59/2.32
Application.....	Security Alarm Systems.

## BP1.2-12 Battery discharge characteristics (25°C/77°F)



## BATTERY CHARGING CHARACTERISTICS (Typical example of the charge characteristics for the standby use)




### Charging Procedure


Application	Charging method	Charging Voltage at 20°C (V/cell)	Temperature compensation coefficient of charging voltage (mV/°C/cell)	Max. charging current (CA)	Charging time 0.1CA, 20°C (h)		Temp (°C)
					100% discharge	50% discharge	
For standby power source	Constant voltage & Constant current charging (with current restriction)	2.25~2.30	-3	0.3	24	20	0~40 (32~104°F)
For cycle service		2.40~2.50	-4	0.3	16	10	

\*Temperature compensation of charging voltage is not needed, when using the batteries within 5°C to 35°C range.


### Effect of Temperature on Long Term Float Life



### OUTER DIMENSIONS




### TERMINAL TYPE mm (inch)



### Constant power discharge characteristics at 25°C/77°F

Final Voltage	Discharge time								
	5Min	10Min	15Min	30Min	1Hr	3Hr	5Hr	10Hr	20Hr
10.80V	43.4	31.9	25.6	15.2	8.73	3.50	2.41	1.35	0.70
10.50V	50.2	34.6	26.8	15.8	9.00	3.57	2.45	1.37	0.72
10.20V	53.4	35.8	27.6	16.2	9.16	3.60	2.46	1.37	0.72
9.90V	55.8	36.7	28.2	16.4	9.27	3.63	2.47	1.38	0.73
9.60V	57.6	37.4	28.8	16.6	9.36	3.65	2.48	1.38	0.73

### TERMINAL POSITION



**B.B. BATTERY CO., LTD.** Web Site: <http://www.bb-battery.com>

#### USA :

B&B BATTERY (USA) INC.  
6415 RANDOLPH ST. COMMERCE,  
CA, 90040 U.S.A.  
TEL: 1-323-278-1900 . 1-800-278-8599  
FAX: 1-323-278-1268

#### CHINA FACTORY:

CHENG DONG TRIAL AREA, HUANG GANG,  
RAOPING GUANG DONG, CHINA, 515700  
TEL: 86-768-7601001-2  
FAX: 86-768-7601469

#### UK:

B & B BATTERY (UK) CO., LTD.  
TEL: 44-161-339-9458  
FAX: 44-161-343-7030

#### HONG KONG:

NATIONAL TRADING LTD.  
TEL: 852-2301-3800  
FAX: 852-2739-1182

#### JAPAN:

B & B BATTERY (JAPAN) CO., LTD.  
TEL: 81-426-256-537  
FAX: 81-426-256-537

#### TAIWAN:

B & B BATTERY CO., LTD.  
TEL: 886-6-5898081-3  
FAX: 886-6-5898087

